

Table 1: Temperature (in °C) versus time (in minutes) for 90 wt% sn-10 wt% pb alloy

Time	Temperature (°F)	Time	Temperature (°F)	Time	Temperature (°F)
0:00	280	3:10	211	6:20	199
0:10	276	3:20	213	6:30	198
0:20	273	3:30	214	6:40	196
0:30	269	3:40	214	6:50	194
0:40	266	3:50	214	7:00	192
0:50	263	4:00	214	7:10	190
1:00	259	4:10	213	7:20	189
1:10	255	4:20	213	7:30	187
1:20	251	4:30	212	7:40	185
1:30	248	4:40	212	7:50	183
1:40	244	4:50	211	8:00	182
1:50	240	5:00	210	8:10	182
2:00	236	5:10	208	8:20	182
2:10	232	5:20	207	8:30	182
2:20	228	5:30	206	8:40	182
2:30	224	5:40	205	8:50	182
2:40	220	5:50	204	9:00	178
2:50	216	6:00	202	9:10	173
3:00	213	6:10	201	9:20	168